

Технически данни на TIR винил UNITARP - Корея

Item Name			Unitarp 6301	Unitarp 6501	Unitarp 6801
weight			630	650	680
width			2.5	2.5	2.5
fabric			1000X1000	1000X1000	1000X1000
			18X18	20X20	23X23
Surface Lacquering			Top-side	Top-side	Top-side
application			Truck and general covers		
Warranty Year			-	-	-
BASE FABRIC	Testing Method	Unit	POLYESTER	POLYESTER	POLYESTER
YARN	-	dtex	1100X1100	1100X1100	1100X1100
	-	denier	1000X1000	1000X1000	1000X1000
THREAD	-	Fd/cm	7X7	8X8	9X9
	-	Fd/inch	18X18	20X20	23X23
Base Fabric Weight	-	g/sq,m	157	175	200
	-	oz/sq.yd	4.631268437	5.2	5.899705015
THICKNESS	FS 5041	mm	0.49	0.53	0.55
WEIGHT	DIN53352	g/sq,m	630	650	680
	FS 5040	oz/sq.yd	18.5840708	19.1740413	20.05899705
TENSILE STRENGTH(WARP)	DIN 53354	kgf/2"	230	250	300
	FS 5102	lbs/2''''	500	550	660
TENSILE STRENGTH(WEFT)	DIN 53354	kgf/2"	200	230	270
	FS 5102	lbs/2''''	440	500	590
TEAR STRENGTH(WARP)	DIN 53363	kgf/2"	25	30	35
	FS 5134	lbs	55	65	75
TEAR STRENGTH(WEFT)	DIN 53363	kgf/2"	20	25	30
	FS 5134	lbs	45	55	65
ADHESION STRENGTH (WARP)	DIN 53357	kgf/2"	10	10	10
	FS 5970	lbs/2''''	22	22	22